

CLASSIFICATION REPORT

2025AN2737

APPLICANT

ROPRE, LDA
PARQUE INDUSTRIAL DO CANHOSORUA M , LOTE 19
PT-6200-027 COVILHA
Portugal

Att. Rui Pais

IDENTIFICATION AND DESCRIPTION OF SAMPLES

Reference by AITEX	Reference by customer	AITEX sample description
2025AN2737-S01	231 IGN, 231 IGN V, CEILINGO R'BULL Pro 10	Wall covering

TESTS CARRIED OUT

- CLASSIFICATION OF REACTION TO FIRE ACCORDING TO THE STANDARD EN 13501-1:2018.

Tests marked with * are not included within the scope of the ENAC accreditation.

Rev.1 This revision cancels and replaces the previous





RESULTS

CLASSIFICATION OF REACTION TO FIRE ACCORDING TO THE STANDARD EN 13501-1:2018

1. INTRODUCTION

This classification of the report define the classification of the product “**2025AN2737-S01**” according to the procedures given at Standard EN 13501-1:2018.

Product name	2025AN2737-S01
Classification report number	2025AN2737

2. CLASSIFIED PRODUCT DATA

Silver flexible film with bubble core.

2.1 Mounting specifications of Ignitability PQ, according to client

The sample of material has been placed on a standard substrate of fiber cement board with a density of (1800 ± 200) Kg/m³, thickness 8 ± 2 mm and Euroclass A2-s1d0 and adhered to it with acrylic adhesive.

Mounting specifications of SBI, according to client

Product has been mounted with vertical (200mm long wing) and horizontal (500mm long and short wings), the joints are sealed with aluminum tape. The sample has a vertical joint 200 mm from point 0. The sample of material has been placed on a standard substrate of fiber cement board with a density of (1800 ± 200) Kg/m³, thickness (8 ± 2) mm and Euroclass A2-s1d0, and adhered to it with 250 g/m² of a acrylic adhesive.

2.2 Product description according to customer information

Application (final use)	Wall covering
Composition	Layer 1: Aluminium Layer 2: Poliethylene bubble Layer 3: Aluminium
Weight (g/m ²)	Layer 1: 45,5 Layer 2: 509 Layer 3: 45,4
Density (kg/m ³)	Layer 1: 1240 Layer 2: 60 Layer 3: 1240
Thickness (mm)	Layer 1: 0,0366 Layer 2: 7,9 Layer 3: 0,0366

>>>



3. REPORTS AND RESULTS THAT SUSTAIN THIS CLASSIFICATION

3.1 Reports

Laboratory name	Sponsor name	Report reference number	Test method and standard
AITEX	ROPRE, LDA	2025AN2736	EN ISO 11925-2:2020 CEN/TS 15117:2005*
AITEX	ROPRE, LDA	2025AN2736	EN 13823:2020 + A1:2022 CEN/TS 15117:2005*

* Extended application rules taken from product standards and/or technical specifications are not included at laboratory accreditation scope.

3.2 Results

Test method	Test numbers	Parameter	Measurement	Complimented
Direct impingement of small flame EN ISO 11925-2	6	Flame spreads 150 mm	NO	PASS
		Filter paper ignition	NO	PASS
Single Burning Item (SBI) EN 13823	3	FIGRA _{0,2 MJ} (W/s)	5,05	B
		FIGRA _{0,4 MJ} (W/s)	5,05	B
		THR _{600sMJ} (W/s)	0,20	B
		LFS	NO	PASS
		SMOGRA (m ² /s ²)	1,03	s1
		TSP 600s(m ²)	26,73	s1
		Flamming droplets within 600s	NO	d0

>>>



4. CLASSIFICATION AND FIELD OF APPLICATION

4.1 Classification

The product, “**2025AN2737-S01**”, concerning its fire reaction, it is classified

B

Additional classification concerning smoke production is:

s1

Additional classification concerning falling of flaming droplets production is:

d0

Fire reaction classification	B s1 d0
-------------------------------------	----------------

4.2 Extended Field of application

This classification is valid for the following product parameters:

Colour	Colour itself and colouring substance may influence the fire performance of products when tested according to EN ISO 11925-2, EN 13823 y EN ISO 9239-1, because a change of colour may change the absorptivity of the product. If the change of composition is negligible, the influence is negligible. The nature of the colouring substance may also have an influence on the fire behaviour.
Thickness	The thickness of a product will have an influence on the fire performance when tested according to EN ISO 11925-2, EN 13823 and EN ISO 9239-1.
Density	The density of a product will have an influence on the fire performance when tested according to EN ISO 11925-2, EN 13823 y EN ISO 9239-1.
Composition	The composition of a product will have an influence on the fire performance when tested according to EN ISO 11925-2, EN 13823 y EN ISO 9239-1.
Geometry and structure of the product	The geometry and structure of a product will have an influence on the fire performance when tested according to EN ISO 11925-2, EN 13823 y EN ISO 9239-1.
Surface covering or coating	The surface covering or coating of a product on the fire performance when tested according to EN 13823. The surface covering or coating of a product on the fire performance when tested according to EN ISO 11925-2.

5. LIMITATIONS

This classification document does not represent type approval or certification of the product.



Joan Risueño

Head of Fire Behaviour lab.



Date: 21/01/2026 17:26:51

Digitally Signed by: JOAN RISUEÑO CABANES -

NIF: 48605765A

LIABILITY CLAUSES

- 1.- AITEX is liable only for the results of the methods of analysis used, as expressed in the report and referring exclusively to the materials or samples indicated in the same which are in its possession, the professional and legal liability of the Centre being limited to these. Unless otherwise stated, the samples were freely chosen and sent by the applicant.
- 2.- AITEX shall not be liable in any case of misuse of the test materials nor for undue interpretation or use of this document. AITEX laboratories do not carry out sampling.
- 3.- The Offer and / or Order to which the applicant gives approval through signature and seal, constitutes the Legally Executable Agreement in which AITEX is responsible for safeguarding and guaranteeing the absolute confidentiality of the management of all the information obtained or created during the performance of the contracted activities.
- 4.- In the eventuality of discrepancies between reports, a check to settle the same will be carried out in the head offices of AITEX. Also, the applicants undertake to notify AITEX of any complaint received by them as a result of the report, exempting this Centre from all liability if such is not done, the periods of conservation of the samples being taken into account.
- 5.- AITEX is not responsible for the information provided by customers, which is reflected in the Report, and may affect the validity of the results.
- 6.- AITEX will provide at the request of the person concerned, the treatment of complaints procedure.
- 7.- AITEX is not responsible for an inadequate state of the sample received that could compromise the validity of the results, expressing such circumstance, in the test reports.
- 8.- AITEX may include in its reports, analyses, results, etc., any other evaluation which it considers necessary, even when it has not been specifically requested.
- 9.- When a Declaration of Conformity is requested, if not indicated otherwise, the decision rule according to ILAC-G8: 2009 will be applied with a security zone of 1U and a Probability of False Acceptance <2.5%.
- 10.- The uncertainties of tests, which are made explicit in the Results Report, have been estimated for a $k = 2$ (95% probability of coverage). If not informed, they are available to the client in AITEX.
- 11.- The original materials and rests of samples, not subject to test, will be retained in AITEX during the twelve months following the issuance of the report, so that any check or claim which, in his case, wanted to make the applicant, should be exercised within the period indicated.
- 12.- This report may only be sent or delivered by hand to the applicant or to a person duly authorised by the same.
- 13.- The results of the tests and the statement of compliance with the specification in this report refer only to the test sample as it has been analyzed / tested and not the sample / item which has taken the test sample.
- 14.- The client must attend at all times, to the dates of the realization of the tests.
- 15.- According to Resolution EA (33) 31, the test reports must include the unique identification of the sample, and any brand or label of the manufacturer may be added. It is not allowed to re-issue test reports of untested sample names (references), they can only be re-issued for error correction or inclusion of omitted data that were already available at the time of the test. The laboratory can not assume responsibility for declaring that the product with the new trade name / trademark is strictly identical to the one originally tested; This responsibility belongs to the client.
- 16.- This report may not be partially reproduced without the written approval of the issuing laboratory.
- 17.- The tests have been carried out at the Alcoy plant with the address described on the first page of the report, unless another location is indicated in the results sheet of the specific test.